

## lucitelux<sup>®</sup> Light Guide Panel Technical Bulletin

	Test Procedure	Method		Value	Unit
<b>Optical</b>	Luminous Transmittance	ASTM D1003	JIS K 7361-1	93	%
	Haze	ASTM D1003	JIS K 7136	0.5	%
	Refractive Index	ASTM D542	JIS K 7142	1.49	-
<b>Mechanical</b>	Tensile Strength(rupture)	ASTM D638	JIS K 7162	75	MPa
	Elongation @ rupture	ASTM D638	JIS K 7162	4.5	%
	Flexural Strength (rupture)	ASTM D790	JIS K 7171	120	MPa
	Modulus (elasticity)	ASTM D790 ASTM D785	JIS K 7171	3.2	GPa
	Rockwell hardness	ASTM D256	JIS K 7002-2	100	M scale
	Izod (impact)	ASTM D6110	JIS K 7110	2.0	kJ/m <sup>2</sup> kJ/m <sup>2</sup>
	Charpy (impact)		JIS K 7111	17	
<b>Thermal</b>	Specific Heat	-	JIS K 7123	1.5	J/g°C
	Deflection Temperature under load	ASTM D648	JIS K 7191-2	96	°C
	Coefficient of thermal expansion	ASTM D696	JIS K 7197	7.E-05	cm/cm/deg
<b>Electrical</b>	Surface Resistivity	ASTM D257	JIS K 6911	>1E16	Ω/sq
<b>Miscellaneous</b>	Abrasion/Mar resistance (Tabor -100 cycles)	ASTM D4060	JIS K 7204	40	% haze
	Specific gravity	ASTM D792	JIS K 7112	1.19	g/cm <sup>3</sup>
	Water Absorption	ASTM D570	JIS K 7209	0.3	%
	Flammability	UL 94	-	HB	
Intrinsic Viscosity		JIS K 7367-1	cross-linking	l/g	

*The information and recommendations in this document are, to the best of our knowledge, reliable. Users should perform their own tests to determine the suitability of these products for their own particular purposes. Statements made herein should, therefore, not be construed as representations or warranties. The responsibilities of Lucite International, Inc. for claims arising out of breach of warranty, negligence, strict liability, or otherwise is limited to the purchase price of the material. Statements made herein concerning the use of the products or formulations described herein are not to be construed as granting a license to operate under any patent of Lucite International, Inc. or another, or as recommending the infringement of any patent of Lucite International, Inc. or another, and no liability for infringement arising out of any such use is assumed*